

Reporting

Company: Union Steel Manufacturing Company	Date: 10/10/2000
Department:	User Name: Doo Chul Park
Testing Method: ASTM D5796	

Sample ID: Red Panel									
Measurement Type: Line									
Tool Selected: 8 Point Average									
Unit of Measure: Micron			10x Factor : ON						
Position	1	2	3	4	5	6	7	8	Average
Layer1	5	5	4	5	5	5	4	4	5
Layer2	16	15	14	16	14	16	16	15	15
Layer3									
Layer4									
Layer5									
Total Film Build: 20									

