

Reporting

Company : Union Steel Manufacturing Company	Date: 4/11/2000
Department :	User Name: Sang Ho Lee
Testing Method: ASTM D5796	

Sample ID: Sample #7									
Measurement Type: Line									
Tool Selected: 8 Point Average									
Unit of Measure: Micron					10x Factor : ON				
Position	1	2	3	4	5	6	7	8	Average
Layer1	4	6	5	6	7	8	8	5	6
Layer2	16	15	15	16	13	11	12	14	14
Layer3									
Layer4									
Layer5									
Total Film Build : 20									

